

Chemicals contained in products

Package-type

Epson Package name; **VFPGA10H-144 / Halogen free**

JEITA Package name; **(P-VFPGA-144-1010-0.80)**

Solder ball Type; **Lead(Pb) Free**

Weight; **0.16 [g]** *Note1

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content *Note2		Application		
					[mg]	[ppm]			
IC Die	IC Die	5.5	Silicon	7440-21-3	5.5	999914	Base material		
			Boron	7440-42-8	0.00001	2	Dopant		
			Phosphorus	7723-14-0	0.00003	5	Dopant		
			Aluminum	7429-90-5	0.0001	20	Metalization		
			Arsenic *Note3	7440-38-2	0.00003	5	Dopant		
			Fluorine *Note3	7782-41-4	0.00001	2	Dopant		
			Titanium *Note3	7440-32-6	0.0001	20	Metalization		
			Tungsten *Note3	7440-33-7	0.0002	30	Metalization		
			Cobalt *Note3	7440-48-4	0.00001	2	Metalization		
	Stress buffer coat	0.11	Polyimide	-	0.11	1000000	Stress buffer coat *Note4		
Package	Substrate	41.24	Glass-cloth	-	7.20	175310	Reinforcement		
			Barium Sulfate	7727-43-7	1.70	40790	Additive		
			Epoxy resin	-	8.10	197180	Base material		
			Acrylate resin	-	2.40	57800	Base material		
			Pigment	-	1.00	25520	Additive		
			Organic filler	-	0.14	3400	Filler		
			Zinc	7440-66-6	0.038	920	Characteristic preserve		
			Chromium	7440-47-3	0.0012	30	Characteristic preserve		
			Copper	7440-50-8	17.30	419050	Copper foil		
			Nickel	7440-02-0	2.70	64000	Plating		
			Gold	7440-57-5	0.66	16000	Plating		
			Die Bonding material	2.86	Epoxy resin	-	1.90	670000	Adhesive
					Acrylic resin	-	0.96	330000	Adhesive
			Solder ball	28.68	Tin	7440-31-5	27.50	957500	Solder ball
	Silver	7440-22-4			0.96	35000	Solder ball		
	Copper	7440-50-8			0.22	7500	Solder ball		
	Bonding Wire	3.10	Gold	-	3.10	1000000	Conductor		
	Mold resin	78.45	Epoxy resin	-	3.90	50000	Base material		
			Silica	60676-86-0/-	68.50	873000	Filler		
			Carbon black	1333-86-4	0.16	2000	Coloring agent		
			Hardening chemical(ex:Phenol resin)	-	3.90	50000	Base material		
			Organic phosphorous compound	-	0.39	5000	Hardening accelerator		
			Others	-	1.60	20000	Additive		

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

*Note4 The stress buffer coat may not be used depending on the individual model.