

Chemicals contained in products

Package-type

Epson Package name; **PFBGA10U-180 / Halogen free**

JEITA Package name; **(P-TFBGA-180-1010-0.65)**

Solder ball Type; **Lead(Pb) Free**

Weight; **0.19 [g]** *Note1

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content ※2		Application		
					[mg]	[ppm]			
IC Die	IC Die	32.6	Silicon	7440-21-3	32.6	999914	Base material		
			Boron	7440-42-8	0.0001	2	Dopant		
			Phosphorus	7723-14-0	0.0002	5	Dopant		
			Aluminum	7429-90-5	0.0007	20	Metalization		
			Arsenic *Note3	7440-38-2	0.0002	5	Dopant		
			Fluorine *Note3	7782-41-4	0.0001	2	Dopant		
			Titanium *Note3	7440-32-6	0.0007	20	Metalization		
			Tungsten *Note3	7440-33-7	0.001	30	Metalization		
			Cobalt *Note3	7440-48-4	0.0001	2	Metalization		
Package	Stress buffer coat	0.65	Polyimide	-	0.65	1000000	Stress buffer coat *Note4		
	Substrate	38.4	Glass-cloth	-	6.70	175310	Reinforcement		
			Barium Sulfate	7727-43-7	1.60	40790	Additive		
			Epoxy resin	-	7.60	197180	Base material		
			Acrylate resin	-	2.20	57800	Base material		
			Pigment	-	0.97	25520	Additive		
			Organic filler	-	0.13	3400	Filler		
			Zinc	7440-66-6	0.035	920	Characteristic preserve		
			Chromium	7440-47-3	0.0011	30	Characteristic preserve		
			Copper	7440-50-8	16.10	419050	Copper foil		
			Nickel	7440-02-0	2.50	64000	Plating		
			Gold	7440-57-5	0.61	16000	Plating		
			Die Bonding material	2.70	Epoxy resin	-	1.80	670000	Adhesive
					Acrylic resin	-	0.90	330000	Adhesive
			Solder ball	14.09	Tin	7440-31-5	13.50	957500	Solder ball
	Silver	7440-22-4			0.49	35000	Solder ball		
	Copper	7440-50-8			0.10	7500	Solder ball		
	Bonding Wire	1.80	Gold	7440-57-5	1.80	1000000	Conductor		
	Mold resin	99.49	Epoxy resin	-	4.90	50000	Base material		
			Silica	60676-86-0/-	87.00	873000	Filler		
			Carbon black	1333-86-4	0.20	2000	Coloring agent		
			Hardening chemical(ex:Phenol resin)	-	4.90	50000	Base material		
			Organic phosphorous compound	-	0.49	5000	Hardening accelerator		
			others	-	2.00	20000	Additive		

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

*Note4 The stress buffer coat may not be used depending on the individual model.